

SCOPE OF WORK ANSI

Z359.11-2014 Safety Requirements for Full Body Harnesses



ISSUE DATE

DOCUMENT CONTROL NUMBER GFT-OP-10a (6-

November 20th, 2019

March-2017) © 2017 INTERTEK

PAGES

13

SECTION 1 SUMMARY OF

TESTING

TEST REPORT FOR LONDON FALL PROTECTION Date:

December 22/2019


Report No.: 103964877CRT-001

Formatted for reader simplification

TESTS COMPLETED	ANSI/ASSE Z359.12-2009 CLAUSE	STATUS
Surface Finish of Hardware 48 Hour Salt Spray	3.1.1.1	Pass
Gate Face Testing of Snap hook & Carabiner	4.2.1.1.2	Pass
Side Load Testing of Snap hook & Carabiner Gates	4.2.1.1.3	Pass
Minor Axis Testing of Snap hook & Carabiner Gates	4.2.1.1.4	Pass
Tensile Testing of Snap hook & Carabiner Bodies	4.2.1.1.1	Pass
Dynamic Strength Testing	4.2.3.1	Pass
Markings and Instructions	5	Pass

SECTION 2

This test report concludes the work anticipated in the testing phase of your project. If there are any questions regarding this report please contact the undersigned at 607-753-6711.



SEE COMPLETE DATA BELOW

Version: 03-April-2017 Page 3 of 5 Control No.



TEST REPORT FOR LONDON FALL PROTECTION

Report No.: 103964877CRT-003a

July 22nd 2019

3933 US Route 11 Cortland, New York ,USA 13045

Telephone: 607-758-6246

Facsimile: None www.intertek.com

Doug Corum London Fall Protection 1731 Price Grange Road, Stoneville NC 27048, USA Doug@londongarmentmfg.com

Report Number.....: 103964877CRT-003a

Signed Quote Number.....: Qu-00980833

PO Number 52319

Name of Testing Laboratory

Test Specification:

Standard.....: ANSI/ASSE Z359.12-2009

Date(s) of Testing..... 7/2/19

Product Description:

Product Type: Anchorage Connector

Brand Name: LFP

Model Number(s):: CLAW Hook

Date(s) Samples Received 3/18/19

TEST REPORT FOR LONDON FALL

Report No.: 103964877CRT-003a **PROTECTION** Date: 12/22/2019

SECTION 1

SUMMARY OF TESTING

TESTS COMPLETED	ANSI/ASSE Z359.12-2009 CLAUSE	STATUS
Surface Finish of Hardware 48 Hour Salt Spray	3.1.1.1	Pass
Gate Face Testing of Snap hook & Carabiner	4.2.1.1.2	Pass
Side Load Testing of Snap hook & Carabiner Gates	4.2.1.1.3	Pass
Minor Axis Testing of Snap hook & Carabiner Gates	4.2.1.1.4	Pass
Tensile Testing of Snap hook & Carabiner Bodies	4.2.1.1.1	Pass
Dynamic Strength Testing	4.2.3.1	Pass
Markings and Instructions	5	Pass

SECTION 2

This test report concludes the work anticipated in the testing phase of your project. If there are any questions regarding this report please contact the undersigned at 607-753-6711.

COMPLETED BY:	Matthew Stevens	REVIEWED BY:	Andrew Rulison
TITLE:	Technician	TITLE:	Engineering Supervisor
SIGNATURE:	MAGA	SIGNATURE	Moderate
DATE	7/18/19	DATE:	7/22/19

Please see attached test data for details.

TEST REPORT FOR LONDON FALL PROTECTION

Date: July 22nd, 2019

SECTION (TEST)	REQUIREMENT	RESULTS	
(Sample #	1
		Break	NO
		Gate opening	>0.125"
	Gate Face Testing of Snaphook & Carabiner:	date opening	70.125
	Apply a load perpendicular to the face of the gate at a point as	Sample #	2
	close to the nose as possible. Apply a load < 3 inches per minute	Break	NO
3.1.1.3 /	until 3,600 lbs. has been achieved and hold for one minute. While	Gate opening	>0.125"
4.2.1.1.2	the load is applied measure the distance of gate separation at the	date opening	<i>></i> 0.123
	point of minimum clearance. Opening shall not exceed 0.125	Sample #	3
	inches.	· · · · · · · · · · · · · · · · · · ·	NO
	TEST 3 SAMPLES	Break	
	TEST 3 SAMPLES	Gate opening	>0.125"
		Sample #	1
		Break	NO .0.135"
		Gate Opening	<0.125"
		Hin	6mm
	Side Load Testing of Snaphook & Carabiner Gates:	HFn	8mm
	Apply a load parallel to the gate at the midpoint between the	Deformation	2mm
	nose and gate hinge. Measure the height (h initial) from the test	Canada #	2
	bed, apply the load until 3,600 lbs-f is achieved and maintain for 1	Sample #	
2112/		Break	NO NO
3.1.1.3 /	minute. Measure the distance of gate separation with the load	Gate Opening	<0.125"
4.2.1.1.3	applied. Release the load and measure the height (h final) from	Hin	6mm
	the test bed. Determine the permanent deformation (h initial – h	HFn	7mm
	final) of the gate. Gate opening and deformation shall not exceed	Deformation	1mm
	0.125 inches.	Cample #	3
	TEST 3 SAMPLES	Sample #	NO NO
		Break	
		Gate Opening	<0.125"
		Hin	6mm
		HFn	8mm
		Deformation	2mm
2111/		Sample #	1,2,3
3.1.1.1 /	Surface Finish of Hardware 48 Hour Salt Spray (ASTM B117)	Corrosion	NO
8.3	, , , , , , , , , , , , , , , , , , , ,	Function	YES
3.1.1.3 / 4.2.1.1.4	Minor Axis Testing of Snaphook & Carabiner Gates: Apply a load parallel to the inside face of the gate until 3,600 lbs-f is achieved and at a rate < 3 inches per minute. Gate shall not release.	Sample(s) # 1,2,3 Break= NO	
7.2.1.1.4	TEST 3 SAMPLES Tensile Testing of Snaphook & Carabiner Bodies: (Includes Proof Load Test, 4.3.2)		Release= NO
3.1.1.3 / 4.2.1.1.1	Test load to 3,600 lbs-f (proof load) between the bearing points at a rate > 1 minute and maintain the load for a minimum of 1 minute. Then test load to 5,000 lbs-f between the bearing points at a rate > 1 minute and maintain the load for a minimum of 1 minute. The gate shall not release. TEST 3 SAMPLES	Sample(s) # 1,2,3 Break= NO Gate Release= NO	

Report No.: 103964877CRT-003a

TEST REPORT FOR LONDON FALL PROTECTION

Date: July 22nd, 2019

SECTION 5

REVISION HISTORY

REPORT NUMBER	DATE OF REVISION	DESCRIPTION OF CHANGE:	PROJECT OWNER	REVIEWED BY
103964877CRT-003a	7/18/19	Original	Matthew Stevens	Andrew Rulison

Sample Photos





Report No.: 103964877CRT-003a

